

# LENSGUARD 503



BRILLIANT THINKING



INNOVATIVE COATINGS

## TECHNICAL DATA (PC)

Bayer Ratio (a)	11.00
Steel Wool Scratch Resistance (b)	2 psi
Taber Abrasion Test (ASTM1044) (c)	100 cycles — 3.00 500 cycles — 8.00
Pencil Hardness Test (ASTM D 3363, modified) (d)	B

(a)–500 g of abrasive media, 600 cycles

(b)–steel wool #0000, 5 rotations, no scratch

(c)–500 g, CS 10 wheels

(d)–Mitsu-Bishi Hi Uni pencils, Wolf-Wilburn Method — 1000 g @ 45 degrees

**PERFORMANCE COATINGS INTERNATIONAL LABORATORIES**  
600 S Murray Street • Bangor, PA 18013 USA • T: 610-588-7900 F: 610-588-7901 •  
[WWW.PCOATINGSINTL.COM](http://WWW.PCOATINGSINTL.COM)