

LENSGUARD 503

Brilliant Thinking → Innovative Coatings



TECHNICAL DATA (PC)

| | |
|--|--|
| Bayer Ratio (a) | 11.00 |
| Steel Wool Scratch Resistance (b) | 2 psi |
| Taber Abrasion Test (ASTM1044) (c) | 100 cycles — 3.00 500 cycles — 8.00 |
| Pencil Hardness Test (ASTM D 3363, modified) (d) | B |

(a) 500 g of abrasive media, 600 cycles

(b) steel wool #0000, 5 rotations, no scratch

(c) 500 g, CS 10 wheels

(d) Mitsu-Bishi Hi Uni pencils, Wolf-Wilburn Method — 1000 g @ 45 degrees

CONTACT US



610-588-7900



www.vueguard.com
sales@vueguard.com



600 S Murray St.
Bangor, PA 18013, USA